Jiangxi Tiansheng New Materials Co.Ltd (ISO9001 / SGS)
Head: Hedong Economic Development Zone, Ji'an, Jiangxi
Branch: Room 508, Building B, Yuanfen Science and Technology Park, Longhua, Shenzhen

TIS PU SD08 Print and Cut Vinyl

SPECIFICATIONS

Composition	Thickness	Carrier	Finish	Peel
PU	90um(±5)	110um, Non-adhesive	Glossy	Warm / cold

APPLICATIONS

Ink	Eco solvent ink
Applies on	Cotton, polyester, poly/cotton blends, elastane, textile, leather

Transfer setting		
Time	**Temperature**	**Pressure**
8-15 seconds	145-160° C	Medium (3/5 bar)

Cutting setting		
Blade	**Pressure**	**Speed**
45°	45 gf	20 cm/sec

PRODUCT HIGHLIGHTS

Easy to print, cut, weed, and application
Vibrant colors
For applications on light and dark fabrics

HOW TO APPLY?

1. Print, cut, and peel the material.
2. Remove the print to the adhesive carrier and place it on the garment.
3. Heat applies at the conditions shown above.
4. Peel the adhesive carrier at warm or cold.

PACKAGE INFO

Roll (m)	QTY/CTN	CTN size (cm)	CTN N.W. (kg)
0.51*25m	1	54*15*15cm	4.6kg
0.51*50m	1	54*17*17cm	8.2kg
0.61*25m	1	64*15*15cm	4.8kg
0.61*50m	1	64*17*17cm	9.6kg
1.22*50m	1	124*17*17cm	19.2kg
Size can be customized			

CARE AND WASHING RECOMMENDATIONS

Washing Temp.	Wshing Time	Washing Level	Dry cleaning
Up to 40℃	>60 times	Level 4	No
Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 1 years	-5° C - 42° C	Away from sunlight and dust	Vertical

Wait 12 hours after the application before the first wash.
Respect the textile recommendations.
Do not bleach or use aggressive chemical agents.
Maximum washing time on highest temperature not to exceed 12 minutes.

NOTE: Given the large number of inks and printers, we highly recommend to perform a test before launching a production.