Jiangxi Tiansheng New Materials Co.Ltd (ISO9001 / SGS)
Head: Hedong Economic Development Zone, Ji'an, Jiangxi
Branch: Room 508, Building B, Yuanfen Science and Technology Park, Longhua, Shenzhen

TIS SKHF612 Subli-block cut vinyl

SPECIFICATIONS

Composition	Thickness	Carrier	Finish	Peel
PU	100um(±10)	110um, Non-adhesive	Matte	Cold

APPLICATIONS

Cutter	Cutter, plotter
Applies on	Spandex, cotton, polyester, poly/cotton blends, elastane, textile, leather

Transfer setting		
Time	**Temperature**	**Pressure**
8-15 seconds	145-160° C	Medium (3/5 bar)

Cutting setting		
Blade	**Pressure**	**Speed**
45°	45 gf	20 cm/sec

PRODUCT HIGHLIGHTS

Easy cut, weed, and application
Avoid dye migartion
White color available. Other colors are developing.

HOW TO APPLY?

1. Cut, and peel the material.
2. Place it on the garment.
3. Heat applies at the conditions shown above.
4. Peel the carrier at cold.

PACKAGE INFO

Roll (m)	QTY/CTN	CTN size (cm)	CTN N.W. (kg)
0.51*25m	1	54*15*15cm	4.8kg
0.51*50m	1	54*17*17cm	9.6kg
0.61*25m	1	64*15*15cm	5.8kg
0.61*50m	1	64*17*17cm	11.6kg
White color available. Other colors are developing.			
Size can be customized			

CARE AND WASHING RECOMMENDATIONS

Washing Temp.	Wshing Time	Washing Level	Dry cleaning
Up to 40℃	>60 times	Level 4	No
Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 1 years	-5° C - 38° C	Away from sunlight and dust	Vertical

Wait 12 hours after the application before the first wash.
Respect the textile recommendations.
Do not bleach or use aggressive chemical agents.
Maximum washing time on highest temperature not to exceed 12 minutes.

NOTE: Given the large number of cutters and plotters, we highly recommend to perform a test before launching a production.